



CEWELD DUR WC 3000

TYPE	Crushed Tungsten / Cobalt particles for the MAG carbide feeder system.				
ANWENDUNGEN	Dur WC 3000 is used in combination with the MAG proces to develope a sharp and rough surface on cutting tools for steel and or concrete sawing and or crushing applications. These particles can be used in combination with medium hard, extra hard and corrosion resistant filler metals that fits the application.				
EIGENSCHAFTEN	The particles should fall before the solidification in the molten weldpool and become part of the weld deposit, Metal core fluxcored wires are recommended in spray arc to obtain the best results. The torch angle should be in trailing position at about 80 degrees towards the work piece.				
KLASSIFIKATION					
GEEIGNET FÜR	concrete drilling, earth moving tools, recycling bars and hammers, cutting applications, sawing steel and concrete, deepsea wrack sawing, mixing paddles, scraper blades, mining etc....				
ZULASSUNGEN					
SCHWEISSPOSITIONEN					
TYPISCHE CHEMISCHE ANALYSE DES SCHWEISSMETALLS (%)	C	Co	WC		
	5.7	8	Rem.		
MECHANISCHE GÜTEWERTE	Heat Treatment	$R_{P0,2}$ (MPa)	R_m (MPa)	A5 (%)	Hardness
	As Welded				1700 HV
RÜCKTROCKNUNG	Not required				
GAS ACC. EN ISO 14175					