



CEWELD DUR 6 MoW

TYPE	Gas atomized spherical Cobalt-Chromium-Molybdenum-Tungsten powder for 3D printing dental frames and body parts in medical applications																
ANWENDUNGEN	Overlay welding on wear parts that need to outlast new parts where high temperatures combined with corrosion and wear resistance is required. 3D printing of parts for medical applications according class IIa medical device in accordance with annex IX rule 8 of the MDD 93/42/EEC. Composition corresponds to "type 4" CoCr dental material according to EN ISO 22674.																
EIGENSCHAFTEN	Dur 6 Mo is free of Ni, Be. and Cadmium according EN ISO 22674. The alloy offers extreme low friction properties combined with extreme corrosion resistance and excellent wear properties against scaling, abrasion and extreme pressure loads.																
KLASSIFIKATION	EN ISO	22674: Type 4															
GEEIGNET FÜR	Overlay welding on wear parts. 3D printing of parts for medical applications according class IIa medical device in accordance with annex IX rule 8 of the MDD 93/42/EEC. Composition corresponds to "type 4" CoCr dental material according to EN ISO 22674.																
ZULASSUNGEN																	
SCHWEISSPOSITIONEN																	
TYPISCHE CHEMISCHE ZUSAMMENSETZUNG NACH GEWICHT (%)	Cr	Mo	W	Co	Si	Ni	Mn	Fe	C								
	25	5	4	64	1	0.09	0.07	0.35	0.11								
MECHANISCHE GÜTEWERTE																	
RÜCKTROCKNUNG	Not required																
GAS ACC. EN ISO 14175	None																