



CEWELD CuNi10Fe Tig

TYPE	Copper-Nickel alloyed TIG welding wire									
ANWENDUNGEN	The CEWELD® CuNi10Fe Tig is suitable for welding and cladding CuNi-Materials of ISO 17664 and seawater resistant CuZn alloys of ISO 17660 table 3. And also suitable for surfacing on low alloyed and unalloyed steels and grey cast iron.									
EIGENSCHAFTEN	Sound, pore free deposits on ferrous and non-ferrous base materials.									
KLASSIFIKATION	EN ISO	24373: Cu 7061 / CuNi10								
	W.Nr.	2.0873								
	F-nr	37								
GEEIGNET FÜR	CuNi5Fe (2.0862), CuNi10Fe1Mn (2.0872) Cunifer 10, cuni10fe, seawater resistant, marine applications, tubes, pump building, offshore etc.									
ZULASSUNGEN										
SCHWEISSPOSITIONEN	PAPBPCPDPEPFPG									
TYPISCHE CHEMISCHE ANALYSE DES FÜLLMETALLS (%)	C	Si	Mn	P	S	Ti	Fe	Cu	Pb	Ni+Co
	0.02	0.1	1.1	0.01	0.01	0.4	1.5	Rem.	0.01	10
MECHANISCHE GÜTEWERTE	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V			Hardness		
	As Welded		300	34	RT			190		
								80 HB		
RÜCKTROCKNUNG	Not required									
GAS ACC. EN ISO 14175	I1, I3									



CEWELD CuNi10Fe Tig

CUNI10FE TIG 1,6 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663409485
CUNI10FE TIG 2,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663409492
CUNI10FE TIG 2,4 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663409508
CUNI10FE TIG 3,2 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663409515