



CEWELD AA 410

TYPE	AA 410 is a stainless flux cored wire for Hardfacing.					
ANWENDUNGEN	Overlay of carbon and low-alloy steels for resistance to corrosion, erosion, or abrasion.					
EIGENSCHAFTEN	AA 410 has higher hardness and is used in valve seats to obtain better galling resistance. Normally to obtain adequate ductility, preheat and post-weld heat-treatment are required . AA 410 is a martensitic stainless steel that is heat-treatable. It has a nominal weld metal composition of 12% Chromium. These weld deposits are air-hardenable that can normally be heat-treated after welding					
KLASSIFIKATION	AWS EN ISO W.Nr.	A 5.22: E410T0-4 14700: T Fe7 1.4009				
GEEIGNET FÜR	Ferritic 13 % Chrome steel, 1.4000, 1.4001, 1.4002, 1.4003, 1.4006, 1.4008, 1.4021, 1.4024, X6Cr13, X6CrAl13, X10Cr13, X15Cr13, X20Cr13, G-X10Cr13 AISI 410, 420					
ZULASSUNGEN						
SCHWEISSPOSITIONEN	  					
TYPISCHE CHEMISCHE ANALYSE DES SCHWEISSMETALLS (%)	C	Si	Mn	P	Cr	Mo
	0.12	0.8	1.2	0.015	13.5	0.5
MECHANISCHE GÜTEWERTE	Heat Treatment		R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
	As Welded					330 HB
RÜCKTROCKNUNG	Not required					
GAS ACC. EN ISO 14175	M21					



CEWELD AA 410

AA 410 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663413826