



CEWELD AlSi10Cu4

TYPE	Aluminium welding wire 4145 for Tesla							
ANWENDUNGEN	Filler metal for welding of AlCu alloys. Approved alloy for structural repairs of TESLA vehicles. Low melting point and excellent penetration characteristics.							
EIGENSCHAFTEN	Superior resistance to stress corrosion where high temperature properties are required. It is not recommended to use this alloy for welding aluminium alloys with a high magnesium content. Low melting point: 521 - 584°C							
KLASSIFIKATION	AWS	A 5.10: ER4145						
	EN ISO	18273: S Al4145						
	F-nr	22						
GEEIGNET FÜR	EN AW 2219 AlCu6Mn EN AW 2014 AlCu4SiMg 3.1255 EN AW 2036 AlCu2,6Si0,5Mg0,3 EN AC 45000 G-AlSi5Cu3 EN AW 4145 AlSi10Cu4 Structural repairs of TESLA vehicles							
ZULASSUNGEN	CE							
SCHWEISSPOSITIONEN								
TYPISCHE CHEMISCHE ANALYSE DES FÜLLMETALLS (%)	Si	Mn	Cr	Fe	Cu	Zn	Al	Mg
	9.9	0.04	0.01	0.34	3.5	0.02	Rem.	0.03
MECHANISCHE GÜTEWERTE								
RÜCKTROCKNUNG	Not required							
GAS ACC. EN ISO 14175	I1, I3							