



CEWELD AlMg 4.5Mn Tig

certilas® THE FILLER METAL SPECIALIST

| | | | | | | | | | |
|---|---|-------------------------|----------|--------|-------------------------------|------|----------|--|--|
| TYPE | Tig aluminium welding wire with high corrosion resistance | | | | | | | | |
| APPLICATIONS | Filler metal for Magnesium and Manganese alloyed Aluminium with a maximum Magnesium content of 5%. This alloy shows very good mechanical properties that make it ideal for applications in shipyards, in car and railway industry and constructions of reservoirs and tanks. | | | | | | | | |
| PROPERTIES | Excellent weldability and good mechanical strength combined with good corrosion resistance against seawater are typical for this alloy. The weld deposit is free from porosity due to the special shaving process and cleaning method during production. AlMg4,5Mn is one of the highest grades within the range of aluminum alloys and covers a huge range of alloys. Thicker sections should be preheated (150°C) prior to welding. | | | | | | | | |
| CLASSIFICATION | AWS A 5.10: ER5183 EN ISO 18273: S Al 5183 (AlMg4,5Mn0,7(A)) F-nr 22 | | | | | | | | |
| SUITABLE FOR | Aluminium alloys: AlMg4,5Mn, AlMg5, AlMg2Mn0,8, AlZnMg1, AlZnMgCu0,5, AlMgSi0,5, AlMgSi1, G-AlMg10, G-AlMg5, G-AlMg3Si, G-AlMg5Si, 3.3545, 3.3547, 3.3535, 3.3555, 3.3206, 3.3210, 3.2315, 3.3211, 3.4335, EN AW 5086, EN AW 5083, EN AW 5019, EN AW 5019, EN AW 6060, EN AW 6005A, EN AW 6082, EN AW 6061, EN AW 7020, EN AC 51300, EN AC 51400, | | | | | | | | |
| APPROVALS | CE | | | | | | | | |
| WELDING POSITIONS | | | | | | | | | |
| TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%) | Si | Mn | Cr | Ti | Fe | Al | Mg | | |
| | 0.07 | 0.7 | 0.1 | 0.09 | 0.15 | Rem. | 4.5 | | |
| MECHANICAL PROPERTIES | Heat Treatment | R _{P0,2} (MPa) | Rm (MPa) | A5 (%) | Impact Energy (J) ISO-V RT | | Hardness | | |
| | As Welded | 140 | 300 | 25 | 30 | | HRc | | |
| REDRYING | Not required | | | | | | | | |
| GAS ACC. EN ISO 14175 | I1, I3 | | | | | | | | |