



CEWELD 904L Tig

TYPE	Solid stainless steel austenitic filler metal with excellent corrosion resistance for Tig welding																		
APPLICATIONS	CEWELD® 904L Tig is a corrosion-resistant, solid chromium-nickel-molybdenum-copper wire for welding austenitic stainless alloys with 20% Cr, 25% Ni, 5% Mo, 1.5% Cu, and low carbon content. Typical applications include process vessels and tanks, piping systems, agitators and rotors, as well as cast pumps and valves for the production of fertilizers, phosphoric, sulfur, and acetic acids. It is also suitable for brackish and seawater environments and in some offshore applications.																		
PROPERTIES	CEWELD® 904L Tig can also be used to join Type 317L materials when improved corrosion resistance in certain media is required. To reduce the tendency to crack and hot crack, the low-melting components such as carbon, silicon, and phosphorus in this alloy are limited to a lower content. Good general corrosion resistance similar to that of similar steels/ cast steels, especially in reducing environments. Max. operating temperature 350°C.																		
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.9: ER385</td> </tr> <tr> <td>EN ISO</td> <td>14343-A: W 20 25 5 Cu L</td> </tr> <tr> <td>W.Nr.</td> <td>1.4539</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>5</td> </tr> </table>	AWS	A 5.9: ER385	EN ISO	14343-A: W 20 25 5 Cu L	W.Nr.	1.4539	F-nr	6	FM	5								
AWS	A 5.9: ER385																		
EN ISO	14343-A: W 20 25 5 Cu L																		
W.Nr.	1.4539																		
F-nr	6																		
FM	5																		
SUITABLE FOR	<p>1.4539 / 904L CrNiMoCu / 20 25 5 Cu L 1.4465, 1.4500, 1.4505, 1.4506, 1.4519, 1.4531, 1.4536, 1.4537, 1.4538, 1.4539, 1.4573, 1.4585, 1.4586 X1CrNiMoN25-25-2, X1NiCrMoCu 25-20-5, X1CrNiMoCuN 25-25-5, X2NiCrMoCuN25-20-5, X2NiCrMoCuN20-18, X4NiCrMoCuNb 20-18-2, X5NiCrMoCuTi20-18, X5NiCrMoCuNb22-18 ASTM A182, UNS N08904, S31726 Uranus B6, AISI 904L, Z2NCDU25-20,</p>																		
APPROVALS	CE																		
WELDING POSITIONS																			
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>Cu</th> </tr> </thead> <tbody> <tr> <td>0.019</td> <td>0.35</td> <td>2</td> <td>0.01</td> <td>0.01</td> <td>20</td> <td>25</td> <td>4.5</td> <td>1.6</td> </tr> </tbody> </table>	C	Si	Mn	P	S	Cr	Ni	Mo	Cu	0.019	0.35	2	0.01	0.01	20	25	4.5	1.6
C	Si	Mn	P	S	Cr	Ni	Mo	Cu											
0.019	0.35	2	0.01	0.01	20	25	4.5	1.6											
MECHANICAL PROPERTIES	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{P0,2} (MPa)</th> <th rowspan="2">R_m (MPa)</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th colspan="2">RT</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>410</td> <td>600</td> <td>35</td> <td colspan="2">120</td> <td>HRc</td> </tr> </tbody> </table>	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness	RT		As Welded	410	600	35	120		HRc		
Heat Treatment	R _{P0,2} (MPa)					R _m (MPa)	A ₅ (%)		Impact Energy (J) ISO-V		Hardness								
		RT																	
As Welded	410	600	35	120		HRc													
REDRYING	Not required																		
GAS ACC. EN ISO 14175	I1																		



CEWELD 904L Tig

904L TIG 1,2 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663415349

904L TIG 1,6 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663415356

904L TIG 2,0 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663415363

904L TIG 2,4 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663415370

904L TIG 3,2 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663415387