



CEWELD SG 2

TYPE	ER 70S-6 welding wire for welding un and -low alloyed steels upto 420 MPa yield strength.					
APPLICATIONS	CEWELD® SG2 is a GMAW wire for joining and surfacing unalloyed and low-alloy structural steels. Typical in Shipbuilding, piping, bridges, repair, construction, car-plate welding etc...					
PROPERTIES	CEWELD® SG2 is extreme easy to weld with excellent welding properties. High world wide excepted quality with controlled cast en helix for semi and or semi-automatic applications. Weldable with Co2 and Mix gas.					
CLASSIFICATION	AWS	A 5.18: ER 70S-6				
	EN ISO	14341-A: G 42 3 C1 3Si1, 14341-A: G 42 4 M21 3Si1				
	W.Nr.	1.5125				
	F-nr	6				
	FM	1				
SUITABLE FOR	Rp< 420 MPa (60ksi) ISO 15608: 1.1(ReH < 275 MPa), 1.2 (275 < ReH < 360 MPa), 1.3 (ReH > 360 MPa < 420 MPa) 1.0035, 1.0038, 1.0039, 1.0044, 1.0112, 1.0116, 1.0130, 1.0145, 1.0253, 1.0254, 1.0255, 1.0258, 1.0259, 1.0319, 1.0345, 1.0345, 1.0345, 1.0348, 1.0352, 1.0418, 1.0420, 1.0425, 1.0425, 1.0425, 1.0451, 1.0452, 1.0453, 1.0457, 1.0459, 1.0460, 1.0461, 1.0486, 1.0490, 1.0491, 1.0619, 1.1100, 1.0409, 1.0421, 1.0426, 1.0429, 1.0430, 1.0436, 1.0473, 1.0481, 1.0482, 1.0484, 1.0505, 1.0545, 1.0546, 1.0562, 1.0566, 1.0570, 1.0578, 1.0581, 1.0582, 1.8902, 1.8912, 1.8932 10Ni14, 12Ni14, 13MnNi6-3, 15NiMn6, S235JR-S355JR, S235JO-S355JO, P195TR1-P265TR1, P195GH-P265GH, L245NB-L360NB, L245MB-L360MB, L415NB, L415MB, WStE 380, WStE 420, S420NL A, B, D, E, A 32-E 36 ASTM A 105, A 106, Gr. A, B; A 283 Gr. A, C; A 285 Gr. A, B, C; A 501, Gr. B; A 573, Gr. 58, 65, 70; A 633, Gr. A, C; A 711 Gr. 1013; API 5 L Gr. B, X42, X52, X60 Domex 315-420MC,MC Plus, ML					
APPROVALS	CE, DB: 42.206.01					
WELDING POSITIONS						
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	P	S	
	0.07	0.85	1.45	0.015	0.015	
MECHANICAL PROPERTIES	Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V	Hardness
					-40°C	
	As Welded	440	560	30	90	HRc
REDRYING	Not required					
GAS ACC. EN ISO 14175	M21, C1					



CEWELD SG 2

SG 2 0,6MM

Packaging	KG/unit	EanCode
D-100	4x1,0	8720663404893
D-200	5	8720663404916
D-300	15	8720663404923

SG 2 0,8MM

Packaging	KG/unit	EanCode
BS-300	15	8720663405029
BS-300 Uncoppered	15	8720663405043
D-100	4x0,8	8720663404954
D-200	5	8720663404992
D-300	15	8720663405005
Drum	250	8720663405012

SG 2 0,9MM

Packaging	KG/unit	EanCode
D-200	5	8720663405081
Drum	250	8720663405074

SG 2 1,0MM

Packaging	KG/unit	EanCode
BS-300	1	8720663405135
BS-300 Uncoppered	15	8720663405173
D-200	5	8720663405142
D-300	15	8720663405180
Drum	250	8720663405197

SG 2 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663405425
BS-300 Uncoppered	15	8720663405487
D-200	5	8720663405456
D-300	15	8720663405463
Drum	250	8720663405494
Drum Uncoppered	250	8720663424778