



CEWELD E 9018-B3

TYPE	Basic electrode for creep resistant steel welding 2,25Cr-1Mo Alloy steels. (Type CrMo2 B , E9018-B3)						
APPLICATIONS	CEWELD® E 9018-B3 is a basic electrode with Cr and Mo alloy for welding 10CrMo9-10 steels. Recommended for welding in: Power generation industry Petrochemical and chemical industry, boilers, Steam boilers and turbine construction.						
PROPERTIES	CEWELD® E 9018-B3 is recommended for welding creep resistant steels working in temperatures up to 600°C. The Electrode have excellent welding properties with low spatter formation and very stable arc. Suitable for welding in all positions except vertical down. Excellent gap bridging for root welding. 118% recovery type for economic production of creep resistant steels and pressure-hydrogen-resistant 2¼Cr1Mo-steels.						
CLASSIFICATION	AWS	A 5.5: E 9018-B3					
	EN ISO	3580-A: E CrMo2 B 42 H5					
	F-nr	4					
	FM	3					
SUITABLE FOR	2,25% Cr, 1% Mo 1.7015, 1.7131, 1.7147, 1.7258, 1.7262, 1.7276, 1.7281, 1.7337, 1.7350, 1.7357, 1.7375, 1.7379, 1.7380, 1.7382, 1.7383, 1.7385, 1.7707, 1.8075 10CrMo9.10, 12CrMo9-10, 10CrSiMoV7, 12CrSiMo8, 30CrMoV9, GS-18CrMo9.10, 15CrMoV5-10, 16CrMo4-4, 15CrMo5, 24CrMo5, 22CrMo4-4, GS-17CrMo5-5, 15Cr3, 16MnCr5, 20MnCr5, 10CrSiV7, G19CrMo9-10, 16CrMo9-3, 11CrMo9-10, 10CrMo11 ASTM: A 387 Gr. 22, A217 Grade WC9, A335 Gr. P22, A217 Gr. WC9, A182 F22, A182 T22, A1031 Gr.5015, A1031 Gr.5115, A1031 Gr.4820						
APPROVALS	CE						
WELDING POSITIONS	     						
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	P	S	Cr	Mo
	0.06	0.5	0.9	0.025	0.02	2.4	1
MECHANICAL PROPERTIES	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
					RT		
	690°C±15°C 1h	550	630	22	150		HRc
REDRYING	400°C / 1 hr						
GAS ACC. EN ISO 14175							



CEWELD E 9018-B3

E 9018-B3 2,5 X 350MM

Packaging	KG/unit	EanCode
Can	2,6	8720663400499

E 9018-B3 3,2 X 350MM

Packaging	KG/unit	EanCode
Can	2,6	8720663400529

E 9018-B3 4,0 X 450MM

Packaging	KG/unit	EanCode
Can	3,4	8720663400550