



CEWELD 347Si

TYPE	Filler metal for welding Nb stabilized stainless austenitic steels 18/8. (Type 19 9 Nb, 347Si)																
APPLICATIONS	CEWELD® 347Si is designed for welding 18/8 steels, particularly types 321 and 347. It is also compatible with non-stabilized grades such as 304/304L. Typical operating temperatures range from -100 °C to approximately 400 °C. Main application areas include the food processing industry, breweries, pharmaceutical plants, construction, general engineering, and nuclear technology.																
PROPERTIES	CEWELD® 347Si is suitable for low-temperature applications where a low carbon content and controlled ferrite content are recommended. This is demonstrated by its excellent impact strength values of ~200J at -50 °C (>100 J down to -110 °C). CEWELD® 347Si can be welded without preheating at a maximum interpass temperature of 250 °C. Post-weld heat treatment (PWHT) is not necessary. However, CEWELD® 347Si is not recommended for high-temperature structural components where a carbon content between 0.04% and 0.08% is required for creep resistance. In this case, welding consumables from the 347H series are recommended (see CEWELD® 347H).																
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.9: ER347Si</td> </tr> <tr> <td>EN ISO</td> <td>14343-A: G 19 9 Nb Si</td> </tr> <tr> <td>W.Nr.</td> <td>1.4551</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>5</td> </tr> </table>	AWS	A 5.9: ER347Si	EN ISO	14343-A: G 19 9 Nb Si	W.Nr.	1.4551	F-nr	6	FM	5						
AWS	A 5.9: ER347Si																
EN ISO	14343-A: G 19 9 Nb Si																
W.Nr.	1.4551																
F-nr	6																
FM	5																
SUITABLE FOR	<p>ISO 15608: 8.1 (no Mo) 347, 19 9 Nb, 1.4551</p> <p>1.4000, 1.4001, 1.4002, 1.4003, 1.4006, 1.4301, 1.4303, 1.4306, 1.4308, 1.4310, 1.4311, 1.4312, 1.4319, 1.4541, 1.4543, 1.4546, 1.4550, 1.4552, 1.4561, 1.4878</p> <p>X 6 NiTi 18 10, X 6CrNiNb 18 10, G-X 5CrNiNb 18 9, X 5CrNi 18 7, X 2CrNi 19 11, G-X 2CrNi 18 9, X 5CrNi 18 10, X 5CrNi 18 12 G-X, 6CrNi 18 9, X 12CrNi 17 7, G-X 10CrNi 18 8</p> <p>UNS S30400, S30403, S30453, S32100, S34700</p> <p>AISI 347, 321, 302, 304, 304L, 304LN, CF8C</p>																
APPROVALS	TÜV: (12393), CE																
WELDING POSITIONS																	
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>Cr</th> <th>Ni</th> <th>Nb</th> </tr> </thead> <tbody> <tr> <td>0.04</td> <td>0.7</td> <td>1.9</td> <td>19.5</td> <td>10</td> <td>0.6</td> </tr> </tbody> </table>	C	Si	Mn	Cr	Ni	Nb	0.04	0.7	1.9	19.5	10	0.6				
C	Si	Mn	Cr	Ni	Nb												
0.04	0.7	1.9	19.5	10	0.6												
MECHANICAL PROPERTIES	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{P0.2} (MPa)</th> <th rowspan="2">R_m (MPa)</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th>-110°C</th> <th>-60°C</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>420</td> <td>590</td> <td>35</td> <td>150</td> <td>200</td> <td>HRc</td> </tr> </tbody> </table>	Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness	-110°C	-60°C	As Welded	420	590	35	150	200	HRc
Heat Treatment	R _{P0.2} (MPa)					R _m (MPa)	A ₅ (%)		Impact Energy (J) ISO-V		Hardness						
		-110°C	-60°C														
As Welded	420	590	35	150	200	HRc											
REDRYING	Not required																
GAS ACC. EN ISO 14175	M13, M12																