



CEWELD AA 316LM

TYPE Metal cored stainless steel welding wire. (Type 19 2 3LM, 1.4430)

APPLICATIONS CEWELD AA316LM is suitable for welding stainless steels with an alloy content between 16 to 21% Cr, 6 to 13% Ni and up to 3% Mo, stabilised and unstabilised types Widely used in the chemical and food-processing industries, as well as in shipbuilding and various types of architectural structure.

PROPERTIES CEWELD AA316LM offers good general corrosion resistance, particularly to corrosion in acid and chlorinated environments. Low carbon deposit. Enhanced productivity, improved weldability, better wetting properties compared to solid wires. Excellent weld metal quality and X-ray soundness.

CLASSIFICATION

AWS	A 5.22: EC316L
EN ISO	17633-A: T 19 12 3 L M M12 1
W.Nr.	1.4430
F-nr	6
FM	5

SUITABLE FOR ISO 15608: 8.1 Austenitic $\leq 19\%$ Cr , TÜV 1000: Gr. 21-30, 1.4583, 1.4435, 1.4436, 1.4404, 1.4406, 1.4408, 1.4401, 1.4571, 1.4580, 1.4406, 1.4521, 1.4430 X102CrNiMoNb 18 12, X2CrNiMo 18 14 3 (TP), X4CrNiMo 17 13 3, X2CrNiMo 17 12 2 (TP), X 5CrNiMo 19 11 2, X4CrNiMo 17 12 2 (TP), X6CrNiMo 17 12 2, X6CrNiMoNb 17 12 3, X2CrNiMoN 17 12 3 (TP), X2CrMoTi18-2
AISI 316Cb, 316, 316L, 316LN, 316H, 316Ti, 316Cb, 316LN, 318, 444
UNS S31640, S31603, S31653, S31600, S31630, S44400, S31635, S31640

APPROVALS CE

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

C	Si	Mn	P	S	Cr	Ni	Mo
0.02	0.6	1.4	0.02	0.008	20	12	3

MECHANICAL PROPERTIES

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V	Hardness
				-60°C	
As Welded	450	610	35	40	HRc

REDRYING Not required

GAS ACC. EN ISO 14175 I1, M13, M12