



CEWELD E DUR 400 KB

TYPE Basic coated electrode for rebuilding machine parts and buffer layers.

APPLICATIONS Hardfacing, rebuilding, overlays, machine parts, wheels, buffer layers, etc.

PROPRIÉTÉS Outstanding alloy against high impact combined with abrasion including metal to metal friction. The weld deposit of Dur E 400Kb is an exceptional easy to apply alloy without any risk for cracks and can also be applied on austenitic manganese steels. The weld deposit is machinable with tungsten tool tips. Very good weld deposit appearance and outstanding welding properties on both AC and DC+. Preheating is not required.

CLASSIFICATION EN ISO 14700: E Fe1
DIN 8555: E 1-UM-400-P

CONVIENT POUR Rebuilding worn machine parts, Stone crushers, Hammers, Gears, Cams etc.

AGRÉMENTS

POSITIONS DE SOUDAGE



**ANALYSE CHIMIQUE
TYPIQUE DU MÉTAL DE
SOUDURE (%)**

| C | Mn | Cr | Fe |
|-----|------|----|------|
| 0.1 | 0.85 | 3 | Rem. |

PROPRIÉTÉS MÉCANIQUES

| Heat Treatment | R _{p0,2} (MPa) | R _m (MPa) | A5 (%) | Hardness |
|----------------|-------------------------|----------------------|--------|----------|
| As Welded | | | | 400 HB |

ETUVAGE 300°C / 2 hr

GAS ACC. EN ISO 14175



CEWELD E DUR 400 KB

E DUR 400 KB 3,2 X 350MM

| Packaging | KG/unit | EanCode |
|-----------|---------|---------------|
| Can | 2,8 | 8720663401618 |

E DUR 400 KB 4,0 X 450MM

| Packaging | KG/unit | EanCode |
|-----------|---------|---------------|
| Can | 3,2 | 8720663401625 |