


CEWELD SA Nicro 625

TYPE	Nickel - Chromium - Molybdenum alloy for SAW welding.								
APPLICATIONS	SA Nicro 625 is developed for welding and cladding nickel-based alloys such as alloy 625 or similar materials. This alloy can also be used for welding dissimilar nickel-based alloys to each other, to alloyed steels or to stainless steels and for joining 6% molybdenum super austenitic steels.. SA Nicro 625 is most commonly used in the chemical processing industry, pollution control equipment, marine equipment, nuclear reactor components, pump shafts. Also used in the aerospace industry for thrust reverser assemblies, fuel nozzles, after-burners and combustion systems.								
PROPRIÉTÉS	SA Nicro 625 is a solid drawn wire to be used for the submerged arc process in combination with our fused flux FL 880 or agglomerated flux FL 838 or FL 839.								
CLASSIFICATION	AWS	A 5.14: ERNiCrMo-3							
	EN ISO	18274: S Ni 6625 (NiCr22Mo9Nb)							
	W.Nr.	2.4831							
	F-nr	43							
	FM	6							
CONVIENT POUR	Ni 6625 / NiCr22Mo9Nb / 2.4831 W.Nr: 1.4529, 1.4539, 1.4547, 1.4876, 1.4958, 1.5656, 2.4660, 2.4816, 2.4856, 2.4858, X1CrNiMoCuN20-18-7 - X10NiCrAlTi32-20 - X5NiCrAlTi31-20 - NiCr15Fe - NiCr22Mo9Nb - NiCr21Mo - X1NiCrMoCuN25 20 6 - X1NiCrMoCuN25 20 5 - NiCr21Mo - 8XNi9 ASTM: A 533 Gr1 UNS: S31254 - N08800 - N08810 - N06600 - N06625 - N08825 - N08926 - N08020 Alloy 254SMO - Alloy 800 - Alloy 800H - Alloy 600 - Alloy 625 - Alloy 825 - Sanicro 28 - 6Mo								
AGRÉMENTS									
POSITIONS DE SOUDAGE	PA PB PC								
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL D'APPORT (%)	C	Si	Mn	Cr	Ni	Mo	Nb	Ti	Fe
	0.04	0.5	0.5	22	68	9	3.9	0.2	3
PROPRIÉTÉS MÉCANIQUES	Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness		
					RT	-196°C			
	As Welded	470	770	35	80	50		HRc	
ETUVAGE	Not required								
GAS ACC. EN ISO 14175									



CEWELD SA Nicro 625

SA NICRO 625 1,6MM

Packaging	KG/unit	EanCode
K-415	25	8720663412034

SA NICRO 625 2,4MM

Packaging	KG/unit	EanCode
K-415	25	8720663412041

SA NICRO 625 3,2MM

Packaging	KG/unit	EanCode
K-415	25	8720663412058