



CEWELD CuSn6 Tig

TYPE	Alliage d'étain-bronze contenant au minimum 6 % d'étain pour pratiquement toutes les procédures de soudage.					
APPLICATIONS	Chaudières et tubes en cuivre ou alliages de cuivre, soudure au four, etc.					
PROPRIÉTÉS	Très bonne désoxydation. Surfaçage et assemblage du cuivre et des alliages CuSn. Largement utilisé pour le brasage au four. Fil de cuivre allié de haute qualité. Dépôts sains, sans pores et bonne conductivité électrique. Excellente résistance à la corrosion.					
CLASSIFICATION	AWS	A 5.7: ERCuSn-A				
	EN ISO	24373: Cu 5180A / CuSn6P				
	W.Nr.	2.1022				
CONVIENT POUR	Tin bronze alloy of minimally 6% tin for virtually all welding procedures. Very good deoxidisation. Surfacing and joining of Copper and CuSn-alloys. Widely used in oven soldering. Mat.n: 2.1010, 2.1016, 2.1020, 2.1030, 2.1050, 2.1052, 2.1056, 2.1080, 2.1086, 2.1090, 2.1096 CuSn8, CuSn7, CuSn6, CuSn4, G-CuSn7ZnPb, G-CuSn10					
AGRÉMENTS						
POSITIONS DE SOUDAGE	 PA  PB  PC  PD  PE  PF  PG					
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL D'APPORT (%)	P	Fe	Cu	Zn	Pb	Sn
	0.25	0.05	Rem.	0.05	0.01	5.5
PROPRIÉTÉS MÉCANIQUES	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V	Hardness
	As Welded		260	20	RT	
					32	80 HB
ETUVAGE	Non requis					
GAS ACC. EN ISO 14175	I1, I3					



CEWELD CuSn6 Tig

CUSN6 TIG 1,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663422767
CUSN6 TIG 2,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663422781
CUSN6 TIG 2,4 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663422798
CUSN6 TIG 3,2 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663422804
CUSN6 TIG 4,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663422811
CUSN6 TIG 5,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663422828