



CEWELD NiCro FM 53MD Tig

certilas® THE FILLER METAL SPECIALIST

TYPE	Nickel based filler metal against extreme temperature conditions.																										
APPLICATIONS	CEWELD NiCro FM 53MD is used for the gas-tungsten-arc and gas-metal-arc welding of INCONEL alloy 693, and the overlaying of carbon steels and stainless steels to provide a nickel-chromium-aluminum alloy corrosion resistant surface.																										
PROPRIÉTÉS	Excellent welding properties with high build-up capacity and low dilution rate. Excellent resistance against temperature cycling conditions exceeding 1200°C and carburized medias. Excellent fatigue strength and creep properties. The high chromium and aluminum levels provide excellent resistance to metal dusting in chemical and petrochemical applications. The product also provides excellent resistance to carburization, sulfidation, and other high temperature corrosion forms. Welding similar alloys that have to resist extreme high temperature and for cladding steels or stainless steels to obtain a high temperature resistant surface against oxidation.																										
CLASSIFICATION	AWS A 5.14: ERNiCrFeAl-1 EN ISO 18274: S Ni 6693(NiCr29Fe4Al3) F-nr 43 FM 6																										
CONVIENT POUR	Cladding against high temperature, radiant heater tubes, furnace rolls, muffles in bright annealing furnaces (H ₂ atmosphere), rotary kilns, pipe hangers, waste gas components, hydrogen production, methanol and ammonia synthesis, Inconel alloy 693																										
AGRÉMENTS	CE																										
POSITIONS DE SOUDAGE	 PA  PB  PC  PD  PE  PF  PG																										
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL D'APPORT (%)	<table border="1"> <thead> <tr> <th>C</th><th>Si</th><th>Mn</th><th>Cr</th><th>Ni</th><th>Nb</th><th>Fe</th><th>Al</th><th>Nb+Ta</th></tr> </thead> <tbody> <tr> <td>0.1</td><td>0.4</td><td>0.8</td><td>30</td><td>60</td><td>2</td><td>4</td><td>3.5</td><td>2</td></tr> </tbody> </table>									C	Si	Mn	Cr	Ni	Nb	Fe	Al	Nb+Ta	0.1	0.4	0.8	30	60	2	4	3.5	2
C	Si	Mn	Cr	Ni	Nb	Fe	Al	Nb+Ta																			
0.1	0.4	0.8	30	60	2	4	3.5	2																			
PROPRIÉTÉS MÉCANIQUES	<table border="1"> <thead> <tr> <th>Heat Treatment</th><th>R_{P0,2} (MPa)</th><th>Rm (MPa)</th><th>A5 (%)</th><th>Hardness</th></tr> </thead> <tbody> <tr> <td>As Welded</td><td></td><td>760</td><td>45</td><td>HRc</td></tr> </tbody> </table>									Heat Treatment	R _{P0,2} (MPa)	Rm (MPa)	A5 (%)	Hardness	As Welded		760	45	HRc								
Heat Treatment	R _{P0,2} (MPa)	Rm (MPa)	A5 (%)	Hardness																							
As Welded		760	45	HRc																							
ETUVAGE	Not required																										
GAS ACC. EN ISO 14175	I1																										



CEWELD Nicro FM 53MD Tig

certilas® THE FILLER METAL SPECIALIST

NICRO FM 53MD TIG 2,4 X
914MM

Packaging	KG/unit	EanCode
Tube	4,54	8720663418289