



CEWELD OA S-70-T4R

TYPE	Welding wire developed for welding without protective gas with high deposition rate.							
APPLICATIONS	Welding outside in case high speed welding is required and protective gas is not possible or difficult. Suitable for C-Mn steels such as rails, fabrication of machinery, steel framed buildings and or heavy equipment repair. Recommended for butt assembly of rails and crossings.							
PROPRIÉTÉS	CEWELD OA S 71 T8 is able to Weld out of position at extreme currents and offers a Low hydrogen weld deposit. Excellent slag removal and protective gas is not required. High impact strength at low temperatures combined with excellent mechanical properties within a wide range of heat inputs. Usable under AWS D1.8 for use on Demand Critical welds.							
CLASSIFICATION	AWS A 5.20: E70T-4 EN ISO 17632-A: T 38 Z W N 3 H15 F-nr 6 FM 1							
CONVIENT POUR	Rebuilding and joining steel parts that requires good strength and high productivity.							
AGRÉMENTS								
POSITIONS DE SOUDAGE	 PA  PB							
ANALYSE CHIMIQUE TIPIQUE DU MÉTAL DE SOUDURE (%)	C	Si	Mn	P	S	Al		
	0.2	0.2	0.55	0.002	0.002	1.3		
PROPRIÉTÉS MÉCANIQUES	Heat Treatment	$R_{P0,2}$ (MPa)	Rm (MPa)	A5 (%)	Hardness			
	As Welded	450	610	25	HRc			
ETUVAGE	140°C / 24 hr							
GAS ACC. EN ISO 14175								



CEWELD OA S-70-T4R

OA S-70-T4R 2,0MM

Packaging	KG/unit	EanCode
D-300	15	8720663406132