

# CEWELD Powder DUR 6 Mo (Alloy F75)



TYPE	Gas atomized spherical Cobalt-Chromium-Molybdenum alloy.			
APPLICATIONS	PTA and or laser overlay welding on wear parts that need to outlast new parts where high temperatures combined with corrosion and wear resistance is required. 3D printing of parts for medical applications as prostatic implants such as replacement hips and knee condyles.			
PROPRIÉTÉS	CoCrMo alloys are non magnetic and offers extrem resistance against fatigue. The alloy offers excellent polishing characteristics and ensures long tool life.			
CLASSIFICATION	EN ISO 14232-1 Co-Cr-Mo 63/28/6			
CONVIENT POUR	Replacement hips, knee parts, condyles, Gas turbine parts, fuel nozzles, orthopedic implants.			
AGRÉMENTS				
POSITIONS DE SOUDAGE				
ANALYSE CHIMIQUE TIPIQUE DU MÉTAL DE SOUDURE (%)	Co Rem.	Cr 27	Mo 6	Other 2.6
PROPRIÉTÉS MÉCANIQUES				
ETUVAGE	Not required			
GAS ACC. EN ISO 14175				