



CEWELD MA SS 2343 Tig

TYPE	Solid welding wire for hardfacing and rebuilding hotworking tools..						
TOEPASSINGEN	Rebuilding and hardfacing parts that are subject to abrasion combined with higher temperatures.						
EIGENSCHAPPEN	Abrasion combined with higher temperatures.						
CLASSIFICATIE	EN ISO W.Nr.	14700: S Fe3 1.2343					
GESCHIKT VOOR	Hotworking tools, high speed tool steels, HSS, aluminium press molts, dies, stamping tools, cutting tools, shear blades, cutters, knives, scissors.						
GOEDKEURINGEN							
LASPOSITIES							
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C 0.4	Mn 0.4	Cr 5	Mo 1.1	V 0.5	Fe Rem.	Si 1
MECHANISCHE WAARDEN	Heat Treatment As Welded		R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness 55 HRc	
HERDROGEN	Not required						
GAS ACC. EN ISO 14175	I1						



CEWELD MA SS 2343 Tig

MA SS 2343 TIG 1,0 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720682051825

MA SS 2343 TIG 1,6 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663401816

MA SS 2343 TIG 2,0 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663401854

MA SS 2343 TIG 2,4 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663401793

MA SS 2343 TIG 3,0 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663401809