



CEWELD G3

TYPE	Copper-coated filler metal for gas welding (0,5% Ni)																
TOEPASSINGEN	Gas welding of steels that require good impact properties at low temperature.																
EIGENSCHAPPEN	Excellent impact properties at low temperatures due to the addition of Nickel with increased yield strenght.																
CLASSIFICATIE	<table border="0"> <tr> <td>AWS</td> <td>A 5.2: R60</td> </tr> <tr> <td>EN ISO</td> <td>20378: O III</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>1</td> </tr> </table>	AWS	A 5.2: R60	EN ISO	20378: O III	F-nr	6	FM	1								
AWS	A 5.2: R60																
EN ISO	20378: O III																
F-nr	6																
FM	1																
GESCHIKT VOOR	<p>Re ≤ 300 MPa (55 ksi) ISO 15608: 1.1 (ReH < 275 MPa) 1.2 (275 < ReH < 300 MPa) 1.0035, 1.0038, 1.0039, 1.0044, 1.0112, 1.0116, 1.0130, 1.0145, 1.0253, 1.0254, 1.0255, 1.0258, 1.0259, 1.0319, 1.0345, 1.0345, 1.0345, 1.0348, 1.0352, 1.0418, 1.0420, 1.0425, 1.0425, 1.0425, 1.0427, 1.0432, 1.0446, 1.0451, 1.0452, 1.0453, 1.0457, 1.0459, 1.0460, 1.0460, 1.0461, 1.0486, 1.0490, 1.0491, 1.0505, 1.0545, 1.0546, 1.0562, 1.0566, 1.0570, 1.0578, 1.0581, 1.0582, 1.1138, 1.5419, 1.8948</p> <p>C 22.8 S1, S185, S235JRG2, S235JR S235JRH, S275JR, P235S, S235J2G3, P265S, S275J2, P235TR1, P235TR2, P265TR1, P265TR2, P235GH, P235GH, P235GH, P195GH, P245GH, L245ME, GE200, P265GH, P265GH, P265GH, C 22.3, C 21, GE240, P215NL, P 250, P255QL, P265NL, L245NE, C 22.8, P250GH, P275N, S275N, S275NL, GP240GH, P275SL, 21 Mn 6, StE 320.7, St 52.0, P280GH, (X42ME) L290ME, P305GH, P355GH, P295GH, L290NE, S355N, S355NL, P355N, P355NL1, S355J2G3, G21Mn5, G20Mo5, X52QE,</p> <p>ASTM: A 105, A 27 u. A36 Gr. all; A214; A 242 Gr.1-5; A266 Gr. 1, 2, 4; A283 Gr. A, B, C, D; A285 Gr. A, B, C; A299 Gr. A, B; A328; A366; A515 Gr. 60, 65, 70; A516 Gr. 55; A570 Gr. 30, 33, 36, 40, 45; A 572 Gr. 42, 50; A606 Gr. Alle; A607 Gr. 45; A656 Gr. 50, 60; A668 Gr. A, B; A907 Gr. 30, 33, 36, 40; A841; A851 Gr. 1, 2; A935 Gr.45; A936 Gr. 50;</p> <p>API 5 L Gr. B, X42-X52</p>																
GOEDKEURINGEN	CE																
LASPOSITIES																	
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>Ni</th> </tr> </thead> <tbody> <tr> <td>0.1</td> <td>0.1</td> <td>1.1</td> <td>0.4</td> </tr> </tbody> </table>	C	Si	Mn	Ni	0.1	0.1	1.1	0.4								
C	Si	Mn	Ni														
0.1	0.1	1.1	0.4														
MECHANISCHE WAARDEN	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{P0.2} (MPa)</th> <th rowspan="2">R_m (MPa)</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th>RT</th> <th></th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>340</td> <td>470</td> <td>20</td> <td>65</td> <td></td> <td>HRc</td> </tr> </tbody> </table>	Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness	RT		As Welded	340	470	20	65		HRc
Heat Treatment	R _{P0.2} (MPa)					R _m (MPa)	A ₅ (%)		Impact Energy (J) ISO-V		Hardness						
		RT															
As Welded	340	470	20	65		HRc											
HERDROGEN	Not required																
GAS ACC. EN ISO 14175	None																