



CEWELD G2

TYPE Copper-coated unalloyed rod for gas welding

TOEPASSINGEN Gas welding of unalloyed steels with a minimum tensile strength of 400 MPa

EIGENSCHAPPEN Joints are homogenous and soft, the mechanical treatment is very good

CLASSIFICATIE

AWS	A 5.2: R60
EN ISO	20378: O II
W.Nr.	1.0494
F-nr	6
FM	1

GESCHIKT VOOR **Re ≤ 300 MPa (55 ksi) ISO 15608: 1.1(ReH < 275 MPa) 1.2 (275 < ReH < 300 MPa)**
 1.0035, 1.0038, 1.0039, 1.0044, 1.0112, 1.0116, 1.0130, 1.0145, 1.0253, 1.0254, 1.0255, 1.0258, 1.0259, 1.0319, 1.0345, 1.0345, 1.0345, 1.0348, 1.0352, 1.0418, 1.0420, 1.0425, 1.0425, 1.0425, 1.0427, 1.0432, 1.0446, 1.0451, 1.0452, 1.0453, 1.0457, 1.0459, 1.0460, 1.0460, 1.0461, 1.0486, 1.0490, 1.0491, 1.0505, 1.0545, 1.0546, 1.0562, 1.0566, 1.0570, 1.0578, 1.0581, 1.0582, 1.1138, 1.5419, 1.8948
 C 22.8 S1, S185, S235JRG2, S235JR S235JRH, S275JR, P235S, S235J2G3, P265S, S275J2, P235TR1, P235TR2, P265TR1, P265TR2, P235GH, P235GH, P235GH, P195GH, P245GH, L245ME, GE200, P265GH, P265GH, P265GH, C 22.3, C 21, GE240, P215NL, P 250, P255QL, P265NL, L245NE, C 22.8, P250GH, P275N, S275N, S275NL, GP240GH, P275SL, 21 Mn 6, StE 320.7, St 52.0, P280GH, (X42ME) L290ME, P305GH, P355GH, P295GH, L290NE, S355N, S355NL, P355N, P355NL1, S355J2G3, G21Mn5, G20Mo5, X52QE,
ASTM: A 105, A 27 u. A36 Gr. all; A214; A 242 Gr.1-5; A266 Gr. 1, 2, 4; A283 Gr. A, B, C, D; A285 Gr. A, B, C; A299 Gr. A, B; A328; A366; A515 Gr. 60, 65, 70; A516 Gr. 55; A570 Gr. 30, 33, 36, 40, 45; A 572 Gr. 42, 50; A606 Gr. Alle; A607 Gr. 45; A656 Gr. 50, 60; A668 Gr. A, B; A907 Gr. 30, 33, 36, 40; A841; A851 Gr. 1, 2; A935 Gr.45; A936 Gr. 50;
API 5 L Gr. B, X42-X52

GOEDKEURINGEN CE

LASPOSITIES

TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn
	0.1	0.15	1.1

MECHANISCHE WAARDEN	Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V	Hardness
					RT	
	As Welded	320	450	21	50	HRc

HERDROGEN Not required

GAS ACC. EN ISO 14175 None