



CEWELD ER 90 S-G (P92) Tig

TYPE Medium alloyed, high-strength creep resistant 9% Chromium alloy.

TOEPASSINGEN TIG/GTAW wire for high temperature, creep resistant, modified 9%Cr1%Mo martensitic steel (T92/P92). Alloy T92/P92 is widely used in the power generating industry for fossil fuel ultra-super-critical (USC) power plant boilers and turbines; the alloy is also finding applications in the chemical and oil and gas industries.

EIGENSCHAPPEN T92/P92 steel is commonly used at service temperatures up to 620°C. V, Nb and N additions provide this 'creep strength enhanced ferritic' (CSEF) alloy with improved high temperature creep resistance compared to standard CrMo creep resistant alloys.

CLASSIFICATIE

AWS	A 5.28: ER 90S-G
EN ISO	21952-A: W ZCrMoWVNb 9 0,5 1,5
F-nr	6
FM	4

GESCHIKT VOOR **P92: 9%Cr1.7%W0.5%Mo,**
1.4901
X10CrWMoVNB 9 2
ASTM A213 Gr. T 92; A355 Gr. P92; A187 F92, A369 FP92; A1017 Gr 92
KA-STBA29; KA-STPA29 NF 616

GOEDKEURINGEN CE

LASPOSITIES



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

C	Si	Mn	P	S	Cr	Ni	Mo	W	Nb
0.1	0.35	0.5	0.008	0.008	9.1	0.5	0.8	1.6	0.05

MECHANISCHE WAARDEN

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
730°C- 760°C 3h	550	630	17	HRc

HERDROGEN Not required

GAS ACC. EN ISO 14175 I1