



CEWELD SA 1.41 B

TYPE	Medium alloyed seamless basic flux cored wire for SAW			
TOEPASSINGEN	Crane, apparatus, pressure vessels, foundries, casting etc.			
EIGENSCHAPPEN	Extreme crack resistant weld metal due to the high basic slag in combination with a remarkable low hydrogen content. The requirements of the steels mentioned are obtained in normalized (N) and in air quenched (A) condition . SA 1.41 B is not recommended in the stress relieved condition.			
CLASSIFICATIE				
GESCHIKT VOOR	Base metal Fine grain steel N+A -	DIN WStE 315 till 420 StE 315 till StE 420 EStE 315 till EStE 420	EN S315*NL1/2) - S420(NL1/2) - -	ASTM A 516 / A 255 A 333 / A 350 A 612 / A 707
GOEDKEURINGEN				
LASPOSITIES	 			
MECHANISCHE WAARDEN				
HERDROGEN	Not required			
GAS ACC. EN ISO 14175				