



CEWELD OA 600

TYPE	High-alloyed tubular wire on a C-Cr-Mo carbide basis against shock and abrasion.												
TOEPASSINGEN	Rebuilding and hardfacing wornout parts that faces heavy shock and abrasion at the same time.												
EIGENSCHAPPEN	Very good wear resistance against abrasion combined with impact. The deposit gives already a very good hardness in the first layer. The choice for the buffer layer is depending on the base metal and not always necessary.												
CLASSIFICATIE	EN ISO	14700: T Fe4											
GESCHIKT VOOR	55-57 HRc hardfacing alloy against shocks and mineral wear, rollers and crushers, Mineral and brick crushing industry, Screw conveyers, carbide recycling etc.												
GOEDKEURINGEN													
LASPOSITIONS													
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	Cr	Mo	Fe	V						
	0.5	0.9	3	6.5	0.7	Rem.	0.4						
MECHANISCHE WAARDEN	Heat Treatment	R _{P0,2} (MPa)	Rm (MPa)	A5 (%)	Hardness								
	As Welded				56 HRc								
HERDROGEN	140°C / 24 hr												
CURRENT TYPE:	DC+												
GAS ACC. EN ISO 14175													



CEWELD OA 600

OA 600 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403346

OA 600 1,6MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403353

OA 600 2,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403360