



CEWELD Al 99,5 Ti

TYPE	Pure aluminum filler metal for Mig welding				
TOEPASSINGEN	Aluminium wire for welding mostly pure aluminium (maximum 0,5% of alloyed elements). Applications in chemistry, electronics, construction and food industries.				
EIGENSCHAPPEN	This pure aluminum filler metal offers excellent weldability when properly cleaned prior to welding. Heavy parts and thicker plates should be preheated (150°C), prior to welding				
CLASSIFICATIE	AWS	A 5.10: ER1450			
	EN ISO	18273: S Al 1450 (Al99,5Ti)			
	W.Nr.	3.0805			
	F-nr	21			
GESCHIKT VOOR	Cast aluminium special repairs, Pure aluminum Al99,0 Al.99,5 Al.99,7 E-AL. 3.0255, 3.0205				
GOEDKEURINGEN	CE				
LASPOSITIES	      				
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	Si	Mn	Ti	Fe	Al
	0.2	0.01	0.15	0.2	99.6
MECHANISCHE WAARDEN	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness
	As Welded	30	80	40	HRc
HERDROGEN	Not required				
GAS ACC. EN ISO 14175	I1, I3				