



CEWELD AA 310B

TYPE	Basic flux cored stainless steel welding wire for M21 and M20 gas																
TOEPASSINGEN	Common applications include industrial furnaces, annealing chambers, fused salt treatment installations and boiler parts, as well as heat exchangers. Especially where rutile flux cored wire gives a high risk for cracking this basic type is a better choice																
EIGENSCHAPPEN	For welding heat-resistant austenitic steels of the 25% Cr, 20% Ni types. AA 310B has good general oxidation resistance, especially at high temperatures, due to its high Cr content. The alloy is fully austenitic and is therefore sensitive to hot cracking. The temperature limits for use under intermittent oxidation depend on cycle frequency. In no case shall a temperature of 1000°C be exceeded. This alloy can withstand relatively severe thermic shock, and is superior to type 309L																
CLASSIFICATIE	AWS A 5.22: E310T0-4 EN ISO 17633-A: T 25 20 B M21 3 W.Nr. 1.4842 F-nr 6 FM 5																
GESCHIKT VOOR	ISO 15608: 8.1 Austenitic ≤ 19 % Cr, TÜV 1000: Gr. 21-30, Type: 25% Cr, 22%Ni 1.4710, 1.4713, 1.4724, 1.4726, 1.4742, 1.4745, 1.4762, 1.4823, 1.4826, 1.4828, 1.4832, 1.4835, 1.4837, 1.4840, 1.4841, 1.4845, 1.4846, 1.4848, 1.4849, 253MA, X15CrNiSi 25 20, G-X40CrNiSi 25 12, G-X15CrNi 25 20, X8CrNi25-21 AISI 305, 310, 314 ASTM A297 HF / A297HJ																
GOEDKEURINGEN	CE																
LASPOSITIONS																	
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table><thead><tr><th>C</th><th>Si</th><th>Mn</th><th>Cr</th><th>Ni</th></tr></thead><tbody><tr><td>0.1</td><td>0.5</td><td>2.5</td><td>25.5</td><td>21</td></tr></tbody></table>	C	Si	Mn	Cr	Ni	0.1	0.5	2.5	25.5	21						
C	Si	Mn	Cr	Ni													
0.1	0.5	2.5	25.5	21													
MECHANISCHE WAARDEN	<table><thead><tr><th rowspan="2">Heat Treatment</th><th rowspan="2">$R_{P0,2}$ (MPa)</th><th rowspan="2">R_m (MPa)</th><th rowspan="2">A5 (%)</th><th colspan="2">Impact Energy (J) ISO-V</th><th rowspan="2">Hardness</th></tr><tr><th>RT</th><th>80</th></tr></thead><tbody><tr><td>As Welded</td><td>400</td><td>590</td><td>30</td><td></td><td></td><td>HRc</td></tr></tbody></table>	Heat Treatment	$R_{P0,2}$ (MPa)	R_m (MPa)	A5 (%)	Impact Energy (J) ISO-V		Hardness	RT	80	As Welded	400	590	30			HRc
Heat Treatment	$R_{P0,2}$ (MPa)					R_m (MPa)	A5 (%)		Impact Energy (J) ISO-V		Hardness						
		RT	80														
As Welded	400	590	30			HRc											
HERDROGEN	Not required																
GAS ACC. EN ISO 14175	M20, M21																